



TECHNICAL DATA SHEET (TDS)

LLDPE LL50-26

LINEAR LOW DENSITY POLYETHYLENE

OVERVIEW:

Excellent balance of impact strength, rigidity, environmental stress crack resistance and processability.

Applications: food containers, housewares and lids.

Complies with specifications U.S FDA 21 CFR 177.1520 (c) 3.1a.

ADDITIVE:

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10min	50
Density	ASTM D792	g/cm ³	0.926
Properties			
Tensile strength at yield MD	ASTM D638	Psi/MPa	1400/9.65
Tensile strength at Break TD	ASTM D638	Psi/MPa	1100/7.58
Elongation Yield	ASTM D638	%	3.0
Elongation Break	ASTM D638	%	120
Flexural Modulus -2%secant	ASTM D386	Psi/MPa	61000/421
Tensile impact Strengt ²	ASTM D1822	kJ/m ²	189/1822

Film properties are typical of cast film extruded at a melt temperature of 500° F, and a line speed of 800 ft./min.

The above information is provided in good faith. TRANSAMERICAN POLYMERS CORP. is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, TRANSAMERICAN POLYMERS CORP. MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

