



TECHNICAL DATA SHEET (TDS)

PP PP20-01
POLYPROPYLENE

OVERVIEW: Prime Homopolymer intended for use in injection molding applications with fast cycle times, low static charge and high stiffness.

Applications: rigid packaging, housewares, consumer products

Complies with the specifications U.S. FDA 21 CFR 177.1640

ADDITIVE: Nucleant: Yes Antistatic: Yes

Properties	Test Method	Units	Nominal Values
Melt Index 230° C/2.16 Kg	ASTM D1238	g/10min	20.0
Density	ASTM D792	g/cc	0.909
Properties			
Tensile strength at yield (2in/min)	ASTM D638	Psi/MPa	5435/37.5
Tensile strength at Break (2in/min)	ASTM D638	Psi/MPa	2710/18.7
Elongation yield (2 in/min)	ASTM D638	%	8
Elongation Break (2 in/min)	ASTM D638	%	49
Flexural Modulus, 1% secant	ASTM D790A	Psi/MPa	262000/1810
Notched Izod Impact Strength @ 23c	ASTM D256	(ft-lbf/in)/(kj/m2)	0.62/3.27
Hardness Rockwell R	ASTM D785		105
Heat Deflection Temperature @66 Psi (455) kPa	ASTM D648	F/C	237/114
Gloss (60°) angle	ASTM D2457		91
Haze@ 23 C, 50-mil (1.3mm) plaque	ASTM D1003	%	68

Values are intended as guides only, not specifications. Specimens were injection molded

The above information is provided in good faith. TRANSAMERICAN POLYMERS CORP. is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, TRANSAMERICAN POLYMERS CORP. MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

