



TECHNICAL DATA SHEET (TDS)

PP PP36-01NA POLYPROPYLENE

OVERVIEW: Prime Homopolymer intended for use in injection molding applications with fast cycle times, easy mold release.

Applications: closures, appliances, thin walls products

Complies with the specifications U.S. FDA 21 CFR 177.1640

ADDITIVE: Nucleant: Yes Antistatic: Yes

Properties	Test Method	Units	Nominal Values
Melt Index 230° C/2.16 Kg	ASTM D1238	g/10min	35.0
Density	ASTM D792	g/cm ³	0.9
Properties			
Tensile strength at yield (50 mm/min)	ASTM D638	Psi	5800
Elongation yield (50 mm/ min)	ASTM D638	%	6.5
Flexural Modulus (1.3 mm/min) 1% Secant	ASTM D790	psi	270000
Rockwell Hardness, R Scale	ASTM D785		115
Notched Izod Impact Strength @ 73° F	ASTM D256	ft-lbf/in	0.5

Values are intended as guides only, not specifications. Specimens were injection molded

The above information is provided in good faith. TRANSAMERICAN POLYMERS CORP. is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, TRANSAMERICAN POLYMERS CORP. MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

