



TECHNICAL DATA SHEET (TDS)

HDPE DG07-62
HIGH DENSITY POLYETHYLENE

OVERVIEW: Maximum rigidity, high impact strength, top load strength, moderate swell.
Applications: all food packaging applications including holding food during cooking.
Complies with the specifications U.S FDA 21 CFR 177.1520 (C) 2.2

ADDITIVE: Antiblock: None Slip: None

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10min	0.7
Density	ASTM D1505	g/cc	0.961
Properties			
Tensile strength at yield	ASTM D638	Psi/MPa	4365/30
Average Hardness	ASTM D2240	Shore D	65
Flexural Modulus	ASTM D790B	Psi/MPa	250000/1724
Elongation at Break	ASTM D638	%	750
Environmental Stress Crack Resistance 122°f(50°),f50, 100% igepal®	ASTM D 1693	hrs	15
Brittleness Temperature	ASTM D 746	°F (°C)	<-105(<-76)
Deflection Temperature Under Load @66 psi/0.45 Mpa	ASTM D 640	°F (°C)	210(99)

Physical properties measured on compression molded specimens

The above information is provided in good faith. TRANSAMERICAN POLYMERS CORP. is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, TRANSAMERICAN POLYMERS CORP. MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

