



TECHNICAL DATA SHEET (TDS)

HDPE IM20-54
HIGH DENSITY POLYETHYLENE

OVERVIEW: Excellent balance of toughness, stress crack resistance and processability, very narrow molecular weight distribution.

Applications: Injection molding, for injection molded housewares, toys, food containers and pails.

Complies with U.S FDA 21 CFR 177.1520 (C) 3.1a.

ADDITIVE: Antiblock: None Slip: None

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10 min	20
Density	ASTM D792		0.954
Properties			
Tensile strength at Break	ASTM D638	Psi/MPa	2000/14
Tensile strength at Yield	ASTM D638	Psi/MPa	4100/28
Elongation at Break	ASTM D638	%	250
Elongation at Yield	ASTM D638	%	7
Flexural Modulus, 2% secant	ASTM D790B	Psi/MPa	167000/1151
Environment Stress Crack Resistance 122°f(50°),f50, 100% igepal®	ASTM D 1693	Hrs.	3
Hardness, Shore D	ASTM D2240		57
Deflection Temperature Under Load @66 psi/0.45 Mpa	ASTM D 640	°F (°C)	163(73)
Brittleness Temperature	ASTM D 746	°F (°C)	<-105(<-76)
Tensile impact Strength	ASTM D1822, TypeS	Ft,lb/in2(KJ/M ²)	20/42

Physical properties measured on compression molded specimens

The above information is provided in good faith. TRANSAMERICAN POLYMERS CORP. is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, TRANSAMERICAN POLYMERS CORP. MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

