

TECHNICAL DATA SHEET (TDS)

LDPE LD025FRB

LOW DENSITY POLYETHYLENE

OVERVIEW: High melt strength and superior bubble stability, enhances throughputs in LLDPE blends, Superior strength and toughness, excellent shrink film characteristics.

Application: industrial packaging, liners, shrinks film.

Complies with the specification U.S FDA 21 CFR 177.1520 (c) 3.2a

ADDITIVE: Antiblock: None Slip: None

Properties	Test	Units	Nominal
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10 min	0.25
Density	ASTM D792	g/cm ³	0.920
Film Properties			
Tensile strength at break MD	ASTM D882	Psi/MPa	4400/30
Tensile strength at break TD	ASTM D882	Psi/MPa	3000/21
Elongation MD	ASTM D882	%	110
Elongation TD	ASTM D882	%	450
1% Secant Modulus MD	ASTM D882	Psi/MPa	27600/190
1% Secant Modulus TD	ASTM D882	Psi/MPa	33400/230
Haze	ASTM D1003	%	30
Gloss @ 45°	ASTM D2457		20
Dart Drop Impact Strength,	ASTM	g	160

The values were measured on a 38 µm film in a blown film line with 2.5:1BUR and 0.88 mm die gap.

The above information is provided in good faith. TRANSAMERICAN POLYMERS CORP. is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, TRANSAMERICAN POLYMERS CORP. MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

